

Marlex[®] HHM TR-144

High Density Polyethylene

This high molecular weight, hexene copolymer is tailored for blown film applications that require:

- Toughness and durability
- Good processability
- Good blending characteristics with HDPE HMW resins

This resin meets these specifications:

- FDA 21 CFR 177.1520(c) 3.2a
- EU No. 10/2011

Typical applications for HHM TR-144 include:

- T-shirt bags
- Multi-wall liners
- Trash bags

Nominal Resin Properties ^(1,2)	Value (SI Units)	Method
Density	0.946 g/cm ³	ASTM D1505
Melt Index , Condition 190°C / 2.16 kg	0.18 g/10 min	ASTM D1238
Brittleness Temperature , Type A clamp, Type I specimen	<-75°C	ASTM D746
ESCR , Condition B (100% Igepal), F ₅₀	>1000 hrs	ASTM D1693
Flexural Modulus , Tangent - 16:1 span:depth, 12.7 mm/min	1150 MPa	ASTM D790
Nominal Blown Film Properties at 0.025mm ^(1,3)	Value (SI Units)	Method
Dart Drop (66 cm)	90 g	ASTM D1709
Tensile Strength at Yield , 50.8 mm/min MD	24 MPa	ASTM D882
Tensile Strength at Yield , 50.8 mm/min TD	26 MPa	ASTM D882
Elongation at Break , 50.8 mm/min MD	480%	ASTM D882
Elongation at Break , 50.8 mm/min TD	640%	ASTM D882
Elmendorf Tear Strength , MD	19 g	ASTM D1922
Elmendorf Tear Strength , TD	270 g	ASTM D1922

1. The nominal properties reported herein are typical of the product, but do not reflect normal testing variance and therefore should not be used for specification purposes. Values are rounded.
2. The physical properties were determined on compression moulded specimens that were prepared in accordance with Procedure C of ASTM D4703, Annex A1.
3. Based on 0.025 mm film produced at 4:1 blow-up ratio.

Revision Date February 2023

Before using this product, the user is advised and cautioned to make its own determination and assessment of the safety and suitability of the product for the specific use in question and is further advised against relying on the information contained herein as it may relate to any specific use or application. It is the ultimate responsibility of the user to ensure that the product is suited and the information is applicable to the user's specific application. Saudi Polymers Company does not make, and expressly disclaims, all warranties, including warranties of merchantability or fitness for a particular purpose, regardless of whether oral or written, express or implied, or allegedly arising from any usage of any trade or from any course of dealing in connection with the use of the information contained herein or the product itself. The user expressly assumes all risk and liability, whether based in contract, tort or otherwise, in connection with the use of the information contained herein or the product itself. Further, information contained herein is given without reference to any intellectual property issues, as well as any international laws which may be encountered in the use thereof. Such questions should be investigated by the user.