

# SABIC® HDPE B5429

## HIGH DENSITY POLYETHYLENE

### DESCRIPTION

B5429 grade is medium molecular weight High Density Polyethylene copolymer. They are primarily intended for blow molding articles of small sizes. B5429 series grades offer excellent combination of toughness, stress cracking resistance, load bearing strength with easy processability. The grade available with antistatic additive is B5429A.

### TYPICAL APPLICATIONS

B5429 is classified as a multipurpose blow molding grade. It may be blow molded into containers for household and industrial chemicals (eg. Detergents, bleach, fabric softeners, solvents, paints etc), automotive supplies, foodstuffs, toiletries and cosmetics . They can also be used in other hollow thin walled parts and profile extrusions.

### TYPICAL PROPERTY VALUES

Revision 20210719

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>POLYMER PROPERTIES <sup>(1)</sup></b>			
<b>Melt Flow Rate (MFR)</b>			
at 190°C and 2.16 kg	0.3	g/10 min	ASTM D1238
at 190°C and 21.6 kg	29	g/10 min	ASTM D1238
<b>Density at 23°C</b>	954	kg/m <sup>3</sup>	ASTM D1505
<b>MECHANICAL PROPERTIES <sup>(2)</sup></b>			
<b>1% Secant Modulus</b>	1050	MPa	ASTM D638
<b>Tensile Strength at Yield</b>	28	MPa	ASTM D638
<b>Tensile Strength at Break</b>	19	MPa	ASTM D638
<b>Tensile Elongation at Break</b>	>500	%	ASTM D638
<b>Flexural Strength</b>	25	MPa	ASTM D790
<b>Flexural Modulus</b>	1000	MPa	ISO 178/1A
<b>Izod Impact Strength</b>	180	J/m	ASTM D256
<b>Hardness (Shore D)</b>	65	-	ASTM D2240
<b>ESCR (100% Igepal), F50</b>	100	Hrs	ASTM D1693B
<b>ESCR (10% Igepal), F50</b>	60	Hrs	ASTM D1693B
<b>THERMAL PROPERTIES</b>			
<b>Vicat Softening Point</b>	124	°C	ASTM D1525
<b>Brittleness Temperature</b>	<-75	°C	ASTM D746

(1) Typical values: not to be construed as specification limits.

(2) Based on compression molded sheet.

### PROCESSING CONDITIONS

Typical processing conditions for B5429 are:

Barrel temperature: 170 - 200°C

Melt temperature: 190 - 220°C



## STORAGE AND HANDLING

Polyethylene material should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably don't exceed 50°C. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PE resin within 6 months after delivery.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.