

SABIC[®] HDPE B5403

HIGH DENSITY POLYETHYLENE

DESCRIPTION

B5403 is a High Density Polyethylene specially developed for blow molding / Jerry cans and drums. The material offers an excellent combination of stiffness and ESCR and a high Impact resistance. This grade can be used in food contact applications.

TYPICAL APPLICATIONS

B5403 is specially designed for standard jerry cans, UN approved jerry cans, standard drums, L-ring drums for packaging of dangerous goods and UN approved open top drums. This grade can be used in food contact applications.

TYPICAL PROPERTY VALUES

Revision 20190403

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate			
190°C & 21.6 kg load ⁽¹⁾	2.6	g/10 min	ISO 1133
Density at 23°C ⁽¹⁾	954	kg/m ³	ASTM D1505
MECHANICAL PROPERTIES			
Tensile modulus ⁽²⁾	1200	MPa	ASTM D638
Tensile Strength at Yield	27	MPa	ASTM D638
Tensile Strain at Yield	8	%	ISO 527-1/-2
Tensile Impact Strength at -30°C (Notched)	290	kJ/m ²	ISO 8256
Charpy Notched Impact Strength (-30°C, Type 1, Notch A)	80	kJ/m ²	ISO 179
FNCT (3.5 MPa, 2 % Igepal BC/9, 80°C)	14	hrs	ISO 16770

(1) Typical values: not to be construed as specification limits.

(2) Based on compression molded sheet.

PROCESSING CONDITIONS

Recommended processing temperature: 180 - 220°C

HEALTH, SAFETY AND FOOD CONTACT REGULATIONS

Detailed information is provided in the relevant Material Safety Datasheet and or Standard Food Declaration, available on the Internet (www.SABIC.com). Additional specific information can be requested via your local Sales Office.

DISCLAIMER: This product is not intended for and must not be used in any pharmaceutical/medical applications.

STORAGE AND HANDLING

Polyethylene material should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably don't exceed 50°C. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PE resin within 6 months after delivery.



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.